



Aluminum Coil Anodizing Corporation
 501 E Lake Street • Streamwood IL 60107
 Phone: 630-837-4000 • Fax: 630-837-0814
 www.acacorp.com

Product Specification Document

ACAD-487MR-QA Rev 2

Product ID:		487MR/QA UltraWhite High Gloss		
Application:		Lighting Reflectors and Louvers		
Material Specification:				
Alloy:	3XXX			
Temper:	HX4- HX6			
Mechanical Properties (typical):				
Tensile Strength:	162 MPa		(23,500 psi)	
Yield Strength:	152 MPa		(22,000 psi)	
Elongation:	≥3%			
Optical / Anodized Properties:				
Total Reflectance (TR%) ¹ :	86% minimum		¹ (Technidyne TR-2 (ASTM 1651-94))	
Distinctness of Image (DI) ² :	n/a		² (Hunter Labs D47 Dorigon (ASTM E430-83))	
Specular Reflectance (RS) ² :	n/a		³ (DIN 67530)	
15° Diffuseness (15°) ² :	n/a		⁴ (Byk Gardner Micro Gloss Meter)	
Dr. Lange 60° ³ :	w/g	70 min	a/g	n/a
Gardner 60° Gloss ⁴ :	w/g	n/a	a/g	n/a
Anodize Film Thickness ⁵ :	n/a to n/a microns		(n/a to n/a inch)	
Iridescence Rating:	Premium Low Iridescence			
Color ⁶ :	L*	94 to 98	a*	-3 to 1
			b*	-1 to 3
Availability:				
	Sheet and Coil			
Gage:	0.40 to 1.52 mm		(0.016 to 0.060 inch)	
Width:	12.7 to 1341.8 mm		(0.50 to 52.826 inch)	
Length:	up to 3660 mm		(up to 144 inch)	
Tolerances (standard): (Tighter tolerance may be possible. Contact your sales representative.)				
Gage:	From:	0.25 to 0.40 mm	+/- 0.025 mm	(0.010 to 0.016 inch, +/- 0.001 inch)
		0.41 to 0.80 mm	+/- 0.040 mm	(0.017 to 0.032 inch, +/- 0.0015 inch)
		0.81 to 1.00 mm	+/- 0.050 mm	(0.033 to 0.040 inch, +/- 0.002 inch)
Slit Width:	From:	12.5 to 305 mm	+/- 0.125 mm	(0.5 to 12 inch, +/- 0.005 inch)
		306 to 610 mm	+/- 0.38 mm	(12.1 to 24 inch, +/- 0.015 inch)
		611 to 1250 mm	+/- 0.50 mm	(24.1 to 50 inch, +/- 0.020 inch)
Sheet:	Length:	Up to 1524 mm	+/- 1.0 mm	(Up to 60 inch, +/- 0.040 inch)
		1525 to 3050 mm	+/- 1.5 mm	(60 to 120 inch, +/- 0.060 inch)
		3051 to 3660 mm	+/- 2.0 mm	(120 to 144 inch, +/- 0.080 inch)
	Squareness: ¹	Up to 1200 mm	+/- 0.5 mm	(Up to 48 inch, +/- 0.020 inch)
		1201 to 2400 mm	+/- 1.0 mm	(49 to 95 inch, +/- 0.040 inch)
		2401 to 3660 mm	+/- 1.5 mm	(96 to 144 inch, +/- 0.060 inch)
		¹ Difference in diagonals		
Lateral Bow (in one meter):	Width	Under 300 mm: 2.5 mm max.	(Width Under 12 inch: 0.100 inch)	
	Width	Over 300 mm: 1.25 mm max.	(Width Over 12 inch: 0.050 inch)	
Flatness:	Height between waves:	1% of wave length, 8mm (0.32 inch) maximum.		
Burr:	10% of gage	Not to exceed .08 mm (.003 inch)		