



Aluminum Coil Anodizing Corporation
 501 E Lake Street • Streamwood IL 60107
 Phone: 630-837-4000 • Fax: 630-837-0814
 www.acacorp.com

Product Specification Document

ACAD-004MM-MA-JA Rev 1

Product ID: 004MM/MA-JA Black Matte

Application: Architectural Decorative and

Material Specification:

Alloy: 5005

Temper: H34

Mechanical Properties (typical):

Tensile Strength: 165 N/mm² (24,000 psi)

Yield Strength: 145 N/mm² (21,000 psi)

Elongation: 5%

Minimum Bend Radii: 0T

Optical / Anodized Properties:

Color¹: L* 18.00-28.00 a*-2.00-2.00 b* -1.60-0.00 ¹ (Hunter Lab mini-Scan XE Plus)

Gardner 60° Gloss²: With Grain 25-60 Across grain 25-60 ² (BYK Gardner Micro Gloss)

Anodize Film Thickness³: 4.95 – 8.98 Microns (.00020-.00035 Inch) ³ (ASTM B137-89)

Fade 1800 Hours ≤ 5 units ⁴ ⁴ (J1960/J2527)

Availability: Sheet and Coil

Gage: 0.30 to 1.0 mm (0.012 to 0.040 inch)

Width: 12.7 to 1250 mm (0.5 to 49.213 inch)

Length: up to 3660 mm (up to 144 inch)

Tolerances (standard): (Tighter tolerance may be possible. Contact your sales representative.)

Gage:	From:	0.25 to 0.40 mm	+/- 0.025 mm	(0.010 to 0.016 inch, +/- 0.001 inch)
		0.41 to 0.80 mm	+/- 0.040 mm	(0.017 to 0.032 inch, +/- 0.0015 inch)
		0.81 to 1.00 mm	+/- 0.050 mm	(0.033 to 0.040 inch, +/- 0.002 inch)

Slit Width:	From:	12.5 to 305 mm	+/- 0.125 mm	(0.5 to 12 inch, +/- 0.005 inch)
		306 to 610 mm	+/- 0.38 mm	(12.1 to 24 inch, +/- 0.015 inch)
		611 to 1250 mm	+/- 0.50 mm	(24.1 to 50 inch, +/- 0.020 inch)

Sheet:	Length:	Up to 1524 mm	+/- 1.0 mm	(Up to 60 inch, +/- 0.040 inch)
		1525 to 3050 mm	+/- 1.5 mm	(60 to 120 inch, +/- 0.060 inch)
		3051 to 3660 mm	+/- 2.0 mm	(120 to 144 inch, +/- 0.080 inch)

Squareness: ¹	Up to 1200 mm	+/- 0.5 mm	(Up to 48 inch, +/- 0.020 inch)	
		1201 to 2400 mm	+/- 1.0 mm	(49 to 95 inch, +/- 0.040 inch)
		2401 to 3660 mm	+/- 1.5 mm	(96 to 144 inch, +/- 0.060 inch)

¹ Difference in diagonals

Lateral Bow (in one meter):	Width Under 300 mm: 2.5 mm max.	(Width Under 12 inch: 0.100 inch)
	Width Over 300 mm: 1.25 mm max.	(Width Over 12 inch: 0.050 inch)

Flatness: Height between waves: 1% of wave length, 8mm (0.32 inch) maximum.

Burr: 10% of gage Not to exceed .08 mm (.003 inch)